

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 265/06, 291/02, 279/02	A1	(11) International Publication Number: WO 99/12986 (43) International Publication Date: 18 March 1999 (18.03.99)
(21) International Application Number: PCT/GB98/02703 (22) International Filing Date: 8 September 1998 (08.09.98) (30) Priority Data: 9719060.7 9 September 1997 (09.09.97) GB (71) Applicant (for all designated States except US): IMPERIAL CHEMICAL INDUSTRIES PLC [GB/GB]; Imperial Chemical House, Millbank, London SW1P 3JF (GB). (72) Inventors; and (75) Inventors/Applicants (for US only): McGRAIL, Patrick, Terence [GB/GB]; White Hall Farm, 12 The Lane, Mickleby, Saltburn, Cleveland TS13 5LX (GB). JENKINS, Stephen, Derek [GB/GB]; 71 The Paddock, Stokesley, Middlesbrough, Cleveland TS9 5PN (GB). LINDSAY, Christopher, Ian [GB/GB]; 60 Ash Green, Coulby Newham, Middlesbrough, Cleveland TS8 0UP (GB). EMMERSON, Gordon, Thomas [GB/GB]; 27 Parklands Avenue, Billingham, Cleveland TS23 1DZ (GB). (74) Agents: GIBSON, Sara, Hillary, Margaret et al.; ICI Group Intellectual Property, Wilton, Middlesbrough, P.O. Box 90, Cleveland TS90 8JE (GB).	(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i>	
(54) Title: POLYMER COMPOSITION (57) Abstract A polymer composition, a process for its preparation and a moulded article formed from the polymer composition are claimed. The polymer composition comprises (a) a base polymer which is a poly(alkyl(meth)acrylate); and (b) a rubber toughening agent selected from the group consisting of (i) copolymers of (alkyl) acrylate rubbers (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates (iii) copolymers of vinyl aromatic monomers with conjugated diolefins (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated monomers wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer. The polymer composition has improved impact resistance compared to that of the base polymer and has a unique morphology.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Polymer Composition

The present invention relates to a polymer composition, in particular a composition comprising a base polymer which is a poly(alkyl (meth)acrylate) and a rubber toughening agent.

5 Base polymer such as a poly(alkyl (meth)acrylate), e.g. poly(methyl methacrylate), known as PMMA, can be a relatively brittle material. This detracts from its use in certain applications, e.g. external light clusters for automotive vehicles, where properties such as impact resistance are important. Conventionally, the properties of the base polymer can be improved by the addition of comonomers during its production and/or by the addition of
10 toughening agents. Typically, the toughening agents are small particles having a core-shell structure, e.g. as disclosed in GB-A-2039496. The toughening agents are added as pre-made particles which are then compounded with the base polymer. Such toughening agents are prepared using emulsion phase polymerisation in which each layer is sequentially polymerised one on another. Consequently, due to the complexity of the core-shell manufacturing process,
15 the base polymer so toughened is relatively expensive and is primarily confined for use in specialised applications.

Certain rubber toughening agents are used to improve the properties of polystyrene. EP- 0818481-A2 describes a process for the manufacture of high impact polystyrene (HIPS) materials using low shear mechanical agitation such that the product produced contains large
20 particle sizes of a rubber-like composite phase up to 12 micron for shear rates all lower than 50rpm. These particle sizes are retained when this polymeric mixture is further extruded into an article.

It has now been found that base polymer such as a poly(alkyl (meth)acrylate) as previously described can be toughened by the addition of certain rubber toughening agents
25 which are added during the production of the base polymer. The polymer composition so formed has improved impact resistance compared to that of the base polymer and has a unique morphology.

Accordingly, in a first aspect, the present invention provides a polymer composition comprising

- 30 (a) a base polymer which is a poly(alkyl (meth)acrylate); and
(b) a rubber toughening agent selected from the group consisting of
(i) copolymers of (alkyl) acrylate rubbers
(ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
(iii) copolymers of vinyl aromatic monomers with conjugated diolefins
35 (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated

monomers

wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer.

5 In a second aspect the present invention provides a process for the preparation of a polymer composition comprising

- (a) a base polymer which is a poly(alkyl (meth)acrylate); and
- (b) a rubber toughening agent selected from the group consisting of
 - (i) copolymers of (alkyl) acrylate rubbers
 - 10 (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
 - (iii) copolymers of vinyl aromatic monomers with conjugated diolefins
 - (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated

monomers

wherein the rubber toughening agent is present in the polymer composition as discrete islands
15 substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer which process comprises dissolving the rubber toughening agent in a monomer composition from which the base polymer is to be formed to form a solution, polymerising the monomer composition to form the base polymer and thereby causing the rubber toughening agent to come out of solution so as to form islands within the polymer composition in which are
20 included sub-islands of the base polymer.

In a third aspect the present invention provides a moulded article formed from a polymer composition comprising

- (a) a base polymer which is a poly(alkyl (meth)acrylate); and
- (b) a rubber toughening agent selected from the group consisting of
 - 25 (i) copolymers of (alkyl) acrylate rubbers
 - (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
 - (iii) copolymers of vinyl aromatic monomers with conjugated diolefins
 - (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated

monomers

30 wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer.

For the rubber toughening agent (i) copolymers of (alkyl)acrylate rubbers and (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates include both saturated and
35 unsaturated copolymers

The base polymer may be a homopolymer or a copolymer. Preferably the base polymer contains an alkyl methacrylate, such as a C₁-C₄ alkyl methacrylate, e.g. methyl methacrylate. Particularly preferred is when the base polymer is a copolymer of such an alkyl methacrylate and an alkyl acrylate, such as a C₁-C₄ alkyl acrylate, e.g. ethyl acrylate.

5 The rubber toughening agent may be selected from a wide variety of commercially available and other copolymers. Suitable copolymers of vinyl aromatic monomers with (alkyl) acrylates include styrene-butyl acrylate (St-BA) and styrene-lauryl methacrylate (St-LMA) rubbers, preferably incorporating allyl unsaturation. Examples of monomers that can provide allyl unsaturation include allyl methacrylate (AMA) and glycidyl methacrylate (GMA). Suitable
10 copolymers of (alkyl) acrylate rubbers include benzyl methacrylate-lauryl methacrylate (BzMA-LMA) rubber also preferably incorporating allyl unsaturation. Suitable copolymers of vinyl aromatic monomers with conjugated diolefins include styrene-butadiene rubbers such as Nipol NS210, polystyrene-polybutadiene block copolymers such as Cariflex 1184, S1509, S1013. Suitable copolymers of vinyl aromatic monomers with monoethylenically unsaturated
15 monomers include styrene ethylene butylene styrene (SEBS) copolymer.

It is preferred that the rubber toughening agent contains at least some degree of unsaturation, for example where the rubber toughening agent is a styrene-butylacrylate rubber it is preferred that the level of allyl unsaturation is from 1.5 to 5.0 % (on a molar basis), particularly from 1.5 to 4.5 %, and especially about 2%. Where the rubber toughening agent is
20 selected from saturated rubbers such as styrene-butyl acrylate (St-BA), styrene-lauryl methacrylate (St-LMA) and benzyl methacrylate-lauryl methacrylate (BzMA-LMA) rubbers we find that less of the rubber toughening agent is present in the desired island/sub-island morphology whilst a proportion is present in the form of discrete, separate phase.

The islands of rubber toughening agent are generally circular in cross section and
25 typically up to very large average particle sizes of 250 microns or less in diameter, for example from 10 to 100 microns in diameter. However, where the optical properties of the polymer composition are especially important small diameter islands, e.g. from 2 to 5 microns, are desirable. Therefore it is surprising that when an unsaturated styrene-laurylmethacrylate rubber is used even with islands of up to 10 microns in size the optical properties of the
30 polymer composition remain acceptable whereas a comparable polymer composition containing an unsaturated styrene-butylacrylate rubber is translucent and hazy.

Typically, the rubber toughening agent represents from 1 to 20% preferably from 1 to 10% by weight of the polymer composition. More preferably, the rubber toughening agent represents from 2 to 6% by weight of the polymer composition and in particular about 4%, for
35 example 96% by weight of a base polymer containing methyl methacrylate and with 4% by

weight of a styrene-butadiene rubber.

The polymer composition is prepared by dissolving the rubber toughening agent in a monomer composition from which the base polymer is to be formed, for example a mixture of methyl methacrylate and ethyl acrylate, so as to form a solution. The preparation of the
5 solution may be assisted with stirring or agitation and is usually conducted at room temperature. Polymerisation of the monomer composition is then carried out using conventional bulk polymerisation techniques, for example by the addition of suitable initiators such as lauroyl peroxide and chain transfer agents such as lauryl mercaptan. Preferably the temperature under which the polymerisation is conducted is controlled. Additionally, at least
10 during the initial stages of the polymerisation, e.g. up until about 50%, and preferably up until about 35%, of the monomer composition has been polymerised, a high level of shear may be applied, for example between 100 and 250 rpm, for example about 170rpm. However it is preferred that the polymerisation of the monomer composition is undertaken without stirring.

Alternative polymerisation routes, e.g. by solvent, are not known to give rise to the
15 desired morphology.

The polymer compositions of the present invention can be compression moulded or processed in other conventional ways to form articles having improved impact resistance. In such articles the desired morphology is still apparent although the size of the islands may change. Surprisingly, in some cases, it was found that the particle size of the islands of rubber
20 toughening agent were greatly reduced when the polymer compositions were further processed, for example extruded or injection moulded. For example average particle sizes were found to be reduced from tens of microns to less than 5, particularly 0.01 to 3 micron and especially 0.1 to 1 micron, for example 0.1 to 0.5 micron. Even more surprisingly the extruded or injection moulded articles were found to have properties at least equivalent to the
25 corresponding polymer compositions with much larger particle sizes. In some instances the properties of these moulded articles were found to be enhanced as compared to the polymer compositions.

The polymer compositions as herein described may also contain conventional additives including other modifiers such as the previously described core-shell particles which
30 may then be added at lower than usual levels to achieve the same improved properties.

The present invention is illustrated by reference to the following diagram.

Figure 1 is a Transmission Electron Micrograph (TEM) of a section through a polymer composition of PMMA (96%) with styrene-butadiene (4%) which has been produced with shearing at :70rpm during the initial stage of polymerisation and which shows the desired
35 morphology. The base polymer (1) has discrete islands of rubber toughening agent (2) which

contain sub-islands of base polymer (3).

Figure 2 is a TEM of a section through a polymer composition of the same composition as used in Figure 1 but which has not been sheared during the initial stage of polymerisation.

5 The present invention is further illustrated by reference to the following examples.

Example 1

Preparation of Saturated Poly(alkyl)acrylate Rubber Toughening Agents

In addition to the commercially available rubber toughening agents identified a number of saturated rubbers were synthesised from the following monomer combinations in order to give a close match to the refractive index (Ref Ind) of the base polymer and also to provide a rubber toughening agent that had the requisite solubility characteristics, i.e. soluble in the monomer composition but insoluble in the polymer composition.

MONOMER 1 CHOSEN FROM Styrene (St), Benzyl methacrylate (BzMA)

MONOMER 2 CHOSEN FROM Lauryl methacrylate (LMA), Stearyl Methacrylate (SMA),
15 Butyl Acrylate (BA)

The copolymers were prepared via radical polymerisation in toluene with 2,2-azobisisobutyronitrile (AIBN) initiator at 80 °C to give polymers M_n = ca. 7-8K.

The St-LMA and BzMA-LMA copolymers were shown by NMR to be random with little evidence of compositional drift. The target compositions were those predicted to give a refractive index match with a base polymer of Polymethylmethacrylate and it can be seen that, whilst St-LMA (II) and BzMA-LMA deviate a little from this, the desired refractive index was achieved for St-LMA (I).

The glass transition temperatures (T_g) of the copolymers (measured by Differential Scanning Calorimetry (DSC)) show a negative deviation from those predicted from the homopolymer T_g s of polystyrene (95), polylaurylmethacrylate (-64) and polybenzylmethacrylate (54).

Copolymer	Target Composition	Actual Composition (NMR)	T_g (°C)	$M_n/10^3$	$M_w/10^3$	M_w/M_n	Refractive Index
St-LMA(I)	19.1% St	19.1% St	-74	35	72	2.1	1.5
St-LMA(II)	19.1% St	16.1% St	-74	109	249	2.3	1.5
BzMA-LMA	15.8% BzMA	21.9% BzMA	-72	39	61	1.95	1.49
St-BA		26.3% St	-25	20	33	2.2	1.5

Example 2

Preparation of Unsaturated Poly(alkyl)acrylate Rubber Toughening Agents

In a similar manner to the above synthesised saturated rubber toughening agents, styrene-butyl acrylate-allyl methacrylate (St-BA-AMA; I-III) and styrene-lauryl methacrylate-allyl methacrylate (St-LMA-AMA; IV & V) rubbers were synthesised via radical polymerisation of 50 wt% monomer solutions in toluene using AIBN as the initiator.

The level of allyl methacrylate incorporation and molecular weight control in the St-BA-AMA rubbers was limited by the formation of insoluble gels at levels of AMA in the monomer feed higher than 2-3 wt% or concentrations of AIBN higher than ca. 0.1wt% based on the monomer feed.

- 10 A styrene-butyl acrylate rubber incorporating ca. 2% unsaturated methacrylate groups (VI) was synthesised by copolymerising styrene, butyl acrylate and methacrylic acid (2%) and then reacting the carboxylic acid functionality with glycidyl methacrylate (GMA) to generate pendant methacrylic unsaturation.

The compositions (expressed in wt%) and properties of the above identified 15 unsaturated rubbers are presented in the following table.

Code	St	BA	LMA	AMA	GMA	T _g (°C)	M _n	M _w	M _w /M _n	Ref Ind
I	28.7	70.5		1.1		-23	233	666	2.86	1.51
II	29.1	68.6		2.3		-19	145	818	5.64	1.5
III	23.9	71		2.2		-33	173	822	4.75	1.49
IV	13.2		86.2	0.6		-74	159	389	2.45	1.49
V	14.5		83.7	1.8		-69	311	822	2.64	1.5
VI	13.4	84.6			2	-44	236	99	2.38	

The T_gs of the styrene-butyl acrylate rubbers are generally between ca. -15 & -45 °C, dependent upon the level of styrene incorporation, whereas the T_gs of the styrene-lauryl methacrylate rubbers are generally ca. -70 °C.

The refractive indices of the St-BA-AMA rubbers I & II are higher than the desired 20 target of ca. 1.49 (i.e. the refractive index of PMMA) as a consequence of their high styrene contents whereas those of the St-LMA-AMA copolymers IV & V are closer to the target value.

Example 3

Preparation of Polymer Compositions using Saturated Rubber Toughening Agents from Example 1

- 25 The following route was used to prepare the polymer compositions unless otherwise stated.

St-LMA rubber was dissolved in a mixture of methyl methacrylate: ethyl acrylate (96:4) (herein referred to as PMMA) with stirring or agitation at room temperature. Bulk

polymerisation was then carried out, with no shearing, between glass plates using lauroyl peroxide (0.3 wt %) as the initiator, lauryl mercaptan (0.45 wt %) as the chain transfer agent and employing the following temperature programme to form a cast plaque of 4-6mm thickness:

5 60°C 20 hours
80°C 1.5 hours
100°C 2 hours
130°C 2 hours

The cast plaque was then broken up and compression-moulded at 200°C to produce 10 test-pieces, of 3.2 to 4mm thickness, suitable for physical property assessment.

For the polymer composition gross phase separation was observed which resulted in some of the desired morphology being present.

Example 4

Preparation of Polymer Compositions using Saturated Rubber Toughening Agents from

15 Example 1

The method of preparation was the same as in Example 3 except for the application of shearing during polymerisation (defined as stirring at 170 rpm during the early stages of polymerisation (i.e. <30% monomer conversion)). Polymer compositions of PMMA with St-LMA(II) and BzMA-LMA (4% by wt) did not result in gross phase separation. Mouldings of 20 the polymer compositions were hazy but translucent. The TEM of the PMMA/(4%) (BzMA-LMA) rubber showed that a very irregular morphology existed with some islands containing sub-islands of PMMA but with many islands incorporating no sub-islands and of small size. Solubility tests, i.e. immersing a 1g cutting from a plaque in tetrahydrofuran (15ml) with vigorous agitation for 2 days, showed that no cross-linking was present in these polymer 25 compositions.

Example 5

Preparation of Polymer Compositions using Unsaturated Rubber Toughening Agents from

Example 2

Following the preparation methods in Examples 4 and 3 polymer compositions of 30 PMMA with the unsaturated rubbers I-VI were produced both with and without the application of shearing respectively and were subsequently compression moulded. TEMs of the compression-mouldings of PMMA/rubber showed the desired island/sub-island morphology both with and without shear during polymerisation. With the application of shear the islands were between 0.5 - 10 microns in diameter.

35 The optical properties and solubility characteristics of the compression-moulded cast

blends are summarised in the following table.

Rubber	Rubber % wt in Polymer Composition	Shear @ 170 rpm	Moulding Appearance
I	4	Yes	Translucent
I	8	Yes	Translucent
II	4	Yes	Translucent
II	4	No	Translucent
III	2	Yes	Translucent
IV	4	Yes	Transparent
V	4	No	Transparent
VI	4	No	Transparent

The polymer compositions were subjected to solubility tests which indicated a level of gel formation and hence that the allyl methacrylate or glycidyl methacrylate within the rubber had induced cross-linking within the separated phase. This contrasts with the absence of gel formation in polymer compositions of PMMA with saturated rubbers.

At room temperature, polymer compositions of PMMA with St-BA-AMA are hazy whilst those with St-LMA-AMA were transparent. However, the converse was true at elevated temperatures.

Example 6

10 Preparation of Polymer Compositions using Commercial Rubber Toughening Agents

A polymer composition of PMMA with 4% of Nipol NS210, a styrene-butadiene rubber (25:75) available from Zeon Chemicals, was produced by the methods described in Examples 3 and 4.

The PMMA molecular weight characteristics were $M_n = 260,000$, $M_w = 330,000$ and $M_w/M_n = 1.3$ as measured by Gel Permeation Chromatography (GPC) of a PMMA control. The TEMs of the polymer composition showed the desired island/sub-island morphology wherein the islands had very large diameters, typically greater than 100 microns under polymerisation in non-shear conditions. Particle size was measured by visual inspection of the TEMs.

Example 7

Preparation of Polymer Compositions using Commercial Rubber Toughening Agents

20 Kraton FG1901X, a SEBS rubber incorporating a small amount of succinic anhydride, provided polymer compositions, following the method in Example 3, which had the desired island/sub-island morphology but wherein the islands were of generally smaller diameter and contained less of the PMMA as sub-islands.

Example 8

25 Preparation of Polymer Compositions using Commercial Rubber Toughening Agents

Cariflex 1184, from Shell, a polystyrene-polybutadiene block copolymer (30:70) also

provided a polymer composition, following the method in Examples 3 and 4, of the desired morphology.

Example 9

Mechanical Properties of the Polymer Compositions

5 The mechanical properties of the various polymer compositions prepared in Examples 3 to 8 above are summarised in the Tables below. Unnotched Charpy impact strength (1m/s) was measured according to ISO 179 using an instrumented falling weight apparatus. Linear elastic fracture mechanics measurements (K_{Ic} and ductility factor) were carried out using an instrumented falling weight apparatus at impact rate 1m/s on single edge
10 notched beam samples in a three-point bending geometry. Flexural modulus was measured according to ISO 178 at 1mm/min.

Commercial Rubber	Unnotched Charpy (kJ/m ²)	K_{Ic} (MN ^{-3/2}) 1m/s	Ductility Factor (mm) 1m/s	Flexural Modulus (GPa)
PMMA control	11	1.6	0.12	3
Nipol NS210 (4% - no shear)	26	2.6	0.6	1.4
Nipol NS210 (4% - shear)	38	3.1	1.02	1.8
Nipol NS210 (8% - shear)	23	1.8	0.41	0.5
Kraton FG1901X (4% - no shear)	16			3.1
Cariflex 1184 (4% - no shear)	8	2.1	0.41	
Cariflex 1184 (4% - shear)	23	2.4	0.52	

Synthesised Rubber	Unnotched Charpy (kJ/m ²)	K_{Ic} (MN ^{-3/2}) 1m/s	Ductility Factor (mm) 1m/s	Flexural Modulus (GPa)
St-BA-AMA (1%) (4% - shear)	5.9	2.5	0.41	2.4
St-BA-AMA (2%) (4% - shear)	19	2.3	0.4	2.3
St-BA-AMA (1%) (8% - shear)	5.5		0.49	
Sty-BA (8% - shear)			0.54	
St-LMA (4% - shear)	4.5			

St-LMA-AMA (1%) (4% - shear)	11			2.4
---------------------------------	----	--	--	-----

The above results show improved properties of the PMMA/rubber blends compared to PMMA for PMMA/rubber blends prepared both with and without stirring. For Cariflex 1184 the apparent lack of improvement in unnotched Charpy impact strength compared to PMMA for the blend prepared without stirring is thought to be because of the difficulty of dissolving this 5 rubber in the monomeric matrix prior to polymerisation.

Example 10

Post Processing of the Polymer Compositions

A polymer composition of PMMA with Nipol NS210 (4%) was prepared on a semi-technical scale. The polymer composition was extruded using a Haaka extruder at a screw speed of 10 100rpm with the temperatures of the barrel sections as follows:

Barrel Section	1	2	3	4
Temperature (°C)	60	180	220	230

The table below shows the mechanical properties of this composition compared with PMMA only.

Composition	Unnotched Charpy (kJ/m ²)	K _{1c} at 1m/s (kJ/m ²)	Ductility Factor at 1m/s (mm)	Rubber Island Diameter (microns)
PMMA/rubber blend	36.8	3.89	1.32	0.1 -0.5
PMMA comparative	11	1.57	0.12	

Claims

1. A polymer composition comprising
 - (a) a base polymer which is a poly(alkyl (meth)acrylate); and
 - (b) a rubber toughening agent selected from the group consisting of
 - 5 (i) copolymers of (alkyl) acrylate rubbers
 - (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
 - (iii) copolymers of vinyl aromatic monomers with conjugated diolefins
 - (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated monomers
- 10 wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer.
2. A polymer composition as claimed in claim 1 where the base polymer contains an alkylmethacrylate.
- 15 3. A polymer composition as claimed in either of claims 1 or 2 where the base polymer is a copolymer of an alkyl methacrylate and an alkyl acrylate.
4. A polymer composition as claimed in claims 3 where the base polymer is a copolymer of a C₁-C₄ alkyl methacrylate and a C₁-C₄ alkyl acrylate.
5. A polymer composition as claimed in claim 4 where the base polymer is a copolymer
 - 20 of methyl methacrylate and ethyl acrylate.
6. A polymer composition as claimed in any of claims 1 to 5 where the rubber toughening agent represents from 1 to 20% by weight of the polymer composition.
7. A polymer composition as claimed in any of claims 1 to 6 where the rubber toughening agent represents from 1 to 10% by weight of the polymer composition.
- 25 8. A polymer composition as claimed in any of claims 1 to 7 where the copolymers of (alkyl)acrylate and copolymers of vinyl aromatic monomers with (alkyl) acrylates incorporate allyl unsaturation.
9. A polymer composition as claimed in claim 8 where the level of allyl unsaturation is between 1.5 to 5.0 % on a molar basis.
- 30 10. A polymer composition as claimed in any of claims 1 to 9 where the rubber toughening agent comprises a copolymer of (alkyl) acrylate rubbers.
11. A polymer composition as claimed in any of claims 1 to 7 where the rubber toughening agent comprises a copolymer of a vinyl aromatic monomer with a conjugated diolefin.
- 35 12. A polymer composition as claimed in claim 11 where the rubber toughening agent is

a styrene-butadiene rubber copolymer.

13. A polymer composition as claimed in any of claims 1 to 12 where the islands of rubber toughening agent have an average particle sizes of between 0.01 and 250 microns in diameter.

5 14. A process for the preparation of a polymer composition comprising

- (a) a base polymer which is a poly(alkyl (meth)acrylate); and
- (b) a rubber toughening agent selected from the group consisting of
 - (i) copolymers of (alkyl) acrylate rubbers
 - (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
 - 10 (iii) copolymers of vinyl aromatic monomers with conjugated diolefins
 - (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated

monomers

wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base

15 polymer which process comprises dissolving the rubber toughening agent in a monomer composition from which the base polymer is to be formed to form a solution, polymerising the monomer composition to form the base polymer and thereby causing the rubber toughening agent to come out of solution so as to form islands within the polymer composition in which are included sub-islands of the base polymer.

20 15. A process for the preparation of a polymer composition as claimed in claim 14 where a level of shear between 100 and 250rpm is applied during the initial stages of polymerisation.

16. A moulded article formed from a polymer composition comprising

- (a) a base polymer which is a poly(alkyl (meth)acrylate); and
- (b) a rubber toughening agent selected from the group consisting of
 - 25 (i) copolymers of (alkyl) acrylate rubbers
 - (ii) copolymers of vinyl aromatic monomers with (alkyl) acrylates
 - (iii) copolymers of vinyl aromatic monomers with conjugated diolefins
 - (iv) copolymers of vinyl aromatic monomers with monoethylenically unsaturated


monomers

30 wherein the rubber toughening agent is present in the polymer composition as discrete islands substantially surrounded by the base polymer and in which islands are sub-islands of the base polymer.

17. A moulded article formed from a polymer composition as claimed in claim 16 where the islands of rubber toughening agent have particle sizes of average diameter less than 5
35 microns.

18. A moulded article formed from a polymer composition as claimed in either claim 16 or 17 where the islands of rubber toughening agent have particle sizes of average diameter 0.01 to 3 microns.


Fig.1.



Print Magnification : 10,000

2/2

Fig.2.



Print Magnification 10,000

INTERNATIONAL SEARCH REPORT

Int. Appl. No.

PCT/GB 98/02703

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08F265/06 C08F291/02 C08F279/02

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 3 267 178 A (L-H LEE) 16 August 1966 see claims 1,4 ---	1-4, 11-14, 16-18
A	US 4 080 406 A (KELSEY DONALD ROSS) 21 March 1978 see examples ---	1-7, 11, 12, 14-16
A	US 3 178 489 A (H E LUNK ET AL.) 13 April 1965 see examples ---	1-4, 11-14
A	EP 0 014 574 A (ROHM & HAAS) 20 August 1980 see claims 1-5 -----	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

16 November 1998

Date of mailing of the international search report

25/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Meulemans, R

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 98/02703

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 3267178 A	16-08-1966	NONE	
US 4080406 A	21-03-1978	DE 2716207 A FR 2348234 A GB 1576341 A JP 52124095 A	13-10-1977 10-11-1977 08-10-1980 18-10-1977
US 3178489 A	13-04-1965	NONE	
EP 0014574 A	20-08-1980	US 4230833 A AU 533671 B AU 5508080 A BR 8000772 A CA 1127788 A JP 1485404 C JP 55123612 A JP 63031488 B	28-10-1980 08-12-1983 14-08-1980 21-10-1980 13-07-1982 14-03-1989 24-09-1980 24-06-1988